



**Aage Vestergaard Larsen A/S**

Mere end 45 års erfaring med genanvendelse af plast



# TECHNICAL DATA SHEET

The data should be regarded as indicative and should not be used for specification work. Aage Vestergaard Larsen A/S assumes no legal responsibility for the precision or correctness of the test results.

**Ref** 25638-0  
**Printet by** JS / 04-10-22

## **PP COPO R I 015 BLACK**

**Material Id** 25638  
**Colour** Black  
**Material** Polypropylene copolymer  
**Application** Injection moulding

### **Regenerated raw material**

<b>Physical Properties</b>	<b>Test condition</b>	<b>Value</b>	<b>Unit</b>	<b>Test Method</b>	<b>Remark</b>
<b>Mechanical properties</b>					
Charpy impact strength, notch	(+23 °C)	9,5	Kj/m <sup>2</sup>	ISO 179 /1eA *	
Tensile stress at yield	(50 mm/min: +23 °C)	28	Mpa	ISO 527-1-2 *	
Tensile stress at break	(50 mm/min: +23 °C)	17	Mpa	ISO 527-1-2 *	
Elongation at break	(50 mm/min: +23 °C)	130	%	ISO 527-1-2 *	
E - mod	(1 mm/min: +23 °C)	1170	Mpa	ISO 527-1-2 *	
<b>Rheological properties</b>					
Melt Flow Rate	(230 °C: 2,16 kg)	15	g/10 min	ISO 1133 *	

---

\* Test results are based on the relevant standard as a guideline.